

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2002-075332

(43)Date of publication of application : 15.03.2002

(51)Int.Cl.

H01M 4/02  
C22C 1/10  
H01M 4/04  
H01M 4/38  
H01M 4/62  
H01M 4/66  
H01M 10/40

(21)Application number : 2000-265900

(71)Applicant : SANYO ELECTRIC CO LTD

(22)Date of filing : 01.09.2000


(72)Inventor : FUKUI ATSUSHI  
HASHIMOTO TAKUYA  
NAKAMURA HIROSHI  
FUJIMOTO MASAHISA  
FUJITANI SHIN

(54) NEGATIVE ELECTRODE FOR LITHIUM SECONDARY BATTERY AND METHOD OF MANUFACTURING THE SAME

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a negative electrode for a lithium secondary battery capable of providing high service capacity and having excellent charge and discharge cycle characteristic and a method of manufacturing the same.

SOLUTION: The negative electrode is characterized that it is obtained by sintering mixture of active material 12, which contains silicon and/or silicon alloy, and conductive metal powder 13 on the surface of a collector 11, for which conductive metal foil is used, under reducing atmosphere.



## LEGAL STATUS

[Date of request for examination]

01.06.2004

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

BEST AVAILABLE COPY